НОВАЯ ЭРА НАУКИ И ЗНАНИЙ
МЕЖДУНАРОДНЫЙ НАУЧНЫЙ ЖУРНАЛ
global-science-review.com
editor@global-science-review.com

SYNTHESIS METHODS AND STRUCTURAL FEATURES OF THE Mg-MOF-74 METAL-ORGANIC FRAMEWORK

Urakboyev Bekzod

*Deputy Head of the Educational and Methodological Department, Head of the Methodological Support Division at the Kamoliddin Behzod National Institute of Fine Arts and Design.*urakboyevbekzod@gmail.com

Nurova Nargiza

*School Counselor, Specialized State General Education School No. 10, Tashkent Region.*nargizanurova08@gmail.com

Ochilov Golibjon

*Professor, Head of the Department of Chemistry and Ecology, Kokand State University.*golibjon.ochilov@mail.ru

Bakhronov Khayot

*Professor, Tashkent University of Information Technologies named after Muhammad al-Khwarizmi.*baxronov@mail.ru

Abstract. This literature-based study examines the synthesis methods and pore architecture of Mg-MOF-74. Solvothermal, microwave-assisted, and sonochemical approaches to its preparation are described. The roles of the organic linker and magnesium sites in the formation of one-dimensional channels are elucidated. Solvent exchange and activation procedures that render open metal sites accessible are discussed. The principal techniques for assessing framework crystallinity and porosity are identified. Particular attention is given to the need to control phase composition, dehydration conditions, and material stability upon exposure to moisture.

Keywords: Mg-MOF-74, solvothermal synthesis, microwave-assisted synthesis, sonochemistry, pore structure, open metal sites.

Background and objective. Mg-MOF-74 is of interest as a microporous material that combines a well-defined channel geometry with accessible magnesium sites. Reproducible adsorption properties require control over both crystallization and the removal of guest molecules from the pores. The objective of this study is to systematize published information on the preparation of Mg-MOF-74 and to establish the relationship between synthesis conditions, activation, and the structural characteristics of the material [1-6].

Solvothermal synthesis. The principal starting reagents are magnesium nitrate and 2,5-dihydroxyterephthalic acid. During framework formation, the deprotonated linker connects Mg^{2+} ions through its oxygen atoms. Crystallization procedures employing mixed solvents based on N,N-dimethylformamide, ethanol, and water have been reported. Changes in solvent composition and the heating regime affect crystal nucleation and growth; therefore, the conditions of a particular synthesis protocol should be considered together with the subsequent treatment procedure [1,4].

Role of linker deprotonation. Phase formation depends on the participation of both types of functional groups in the organic component: carboxyl and hydroxyl groups. Dietzel and co-workers demonstrated that varying the amount of base during synthesis produces distinct magnesium coordination polymers, CPO-26-Mg and CPO-27-Mg. In the former, deprotonation occurs predominantly at the carboxyl groups, yielding a nonporous structure. In the latter, deprotonated hydroxyl groups also participate in framework construction, enabling the formation of a microporous structure containing channels [5]. Accordingly, the presence of magnesium and the starting linker in the product does not, by itself, confirm the formation of Mg-MOF-74; the target crystalline phase must be identified.

Intensified synthesis methods. Microwave heating provides an alternative to conventional crystallization. Wu and co-workers obtained MOF-74 samples, including the magnesium-based framework, with smaller particles and a more

uniform particle size distribution. The investigated samples also exhibited a higher specific surface area and micropore volume, while retaining a similar average pore diameter [2]. The sonochemical synthesis of Mg-MOF-74 was reported by Yang and co-workers [3]. This approach broadens the available preparation strategies; however, its effectiveness should be evaluated in terms of crystallinity, accessible porosity, and reproducibility, rather than processing time alone.

Structural features. Activated Mg-MOF-74, also known as CPO-27-Mg, consists of Mg^{2+} ions coordinated by 2,5-dioxido-1,4-benzenedicarboxylate ligands. The framework contains one-dimensional channels with a hexagonal cross-section and a characteristic diameter of approximately 1.16 nm. Magnesium sites are located along the internal channel walls. In the activated state, these sites have vacant coordination positions that are accessible to guest molecules [4]. Structural characterization should therefore be complemented by an assessment of the accessibility of these positions.

Coordination environment of magnesium. In the as-synthesized, solvated framework, the metal nodes are coordinated to oxygen atoms of the linker and to guest molecules. Dehydration liberates coordination positions, allowing Mg^{2+} to interact with molecules entering the channels [5]. An important structural consequence is the combination of an ordered pore architecture with a chemically active internal surface. Channel dimensions describe the available space, whereas the state of the magnesium nodes determines the nature of adsorbate–framework interactions. Pore diameter data should therefore be interpreted together with information on sample composition and the extent of activation [4, 5].

From crystal morphology to internal accessibility. The dimensions observed by electron microscopy describe individual particles or aggregates, whereas the channel diameter describes the internal framework architecture. These two length scales should remain distinct when discussing synthesis-induced changes. Smaller particles may shorten transport distances, but this geometric

advantage is useful only if their internal pores remain accessible. Conversely, a sample with well-defined external crystal faces can still contain residual guest molecules. The microscopy and adsorption measurements reported by Wu and co-workers [2] therefore support a complementary characterization strategy: particle-size analysis should be interpreted alongside measurements that probe internal porosity. This distinction is particularly relevant when comparing powders intended for subsequent shaping or incorporation into composite materials.

Solvent exchange and activation. The product obtained after crystallization contains solvent molecules that occupy the pore space and may coordinate to Mg^{2+}. Washing and solvent exchange precede solvent removal by heating under vacuum. This sequence is required to establish accessible pore volume and open metal sites [1, 4]. The activation regime should follow the relevant synthesis protocol and be accompanied by verification of framework integrity. Incomplete removal of guest molecules complicates comparisons of the textural properties of different samples.

Activation as a structural transformation. Activation should be understood as a controlled transition from a guest-containing framework to an accessible porous solid. Removing physically confined solvent and liberating coordinated magnesium positions are related but conceptually distinct objectives. The dehydration behavior described for CPO-27-Mg [5] demonstrates why the final material cannot be characterized solely by its as-synthesized diffraction pattern. A useful assessment compares the sample before and after activation and records the atmosphere, temperature, treatment duration, and subsequent handling. This approach helps establish whether a change in adsorption accessibility results from guest removal or from an alteration of the framework. It also provides a reproducible basis for selecting conditions for later adsorption experiments.

Thermal and hydrolytic stability. The thermal behavior of CPO-27-Mg has been shown to depend on the heating atmosphere [5]. Treatment conditions in air, an inert gas, and dynamic vacuum should therefore not be regarded as

interchangeable. Exposure of the activated material to water vapor requires particular consideration. DeCoste and co-workers investigated changes in the structure and porosity of Mg-MOF-74 upon moisture exposure and demonstrated the need for a comprehensive assessment of its water stability [6]. In practice, the properties of as-synthesized, activated, and moisture-exposed samples should be compared. Retention of diffraction reflections should be evaluated alongside accessible porosity, since crystalline order and adsorption accessibility describe different aspects of the material's condition.

Structural characterization methods. Powder X-ray diffraction enables phase identification and comparison of the crystalline structure with a reference pattern. Scanning electron microscopy characterizes particle morphology and size, while nitrogen adsorption provides information on accessible porosity [2]. For a comprehensive investigation, these techniques should be complemented by infrared spectroscopy and thermogravimetric analysis to assess the state of the linker and the removal of guest molecules. This combination of measurements distinguishes the retention of crystalline order from the actual accessibility of the internal pore space.

Interpretation of textural measurements. Surface-area and pore-volume values should be reported with the adsorption conditions and the evaluation procedure used to obtain them. The IUPAC recommendations on gas physisorption [8] emphasize that model selection and the applicability of the BET method require careful consideration, especially for microporous solids. A numerical surface area should therefore be treated as a method-dependent descriptor rather than a direct count of open magnesium sites. For Mg-MOF-74, adsorption measurements, diffraction, and spectroscopic evidence answer different questions: accessible space, crystalline order, and the local chemical environment. Their agreement strengthens the structural interpretation, while discrepancies identify aspects of sample preparation or analysis that need further investigation.

Reproducibility criteria. Comparisons of Mg-MOF-74 preparation methods should document the reaction medium composition, reagent ratios, temperature–time profile, washing sequence, and activation conditions. For microwave-assisted and sonochemical approaches, the relevant equipment specifications should also be reported. Recording these parameters is essential for meaningful comparisons between material batches. Changes in particle morphology should not automatically be equated with changes in internal channel dimensions: microscopy and adsorption measurements probe different structural length scales [2]. Comprehensive characterization helps determine whether differences in properties arise from crystal size, pore accessibility, or the state of the metal sites.

Stability under realistic handling conditions. The moisture sensitivity discussed in experimental and thermochemical studies [6, 7] has implications beyond operation in humid gas streams. Exposure during sample transfer, storage, and characterization can also affect the state of an activated specimen. Consequently, comparisons between laboratories should describe how samples were handled after activation. Water adsorption and hydrolytic alteration should not be assumed to be equivalent processes; their consequences must be established through appropriate measurements. The thermodynamic analysis of the MOF-74 family [7] further indicates that metal identity is relevant to water stability, so conclusions obtained for another member of the family should not automatically be assigned to the magnesium framework.

Conclusion. The literature analysis indicates that crystallization conditions and post-synthetic treatment should be regarded as interconnected stages in the preparation of Mg-MOF-74. Solvothermal, microwave-assisted, and sonochemical approaches offer different opportunities for controlling material formation. The principal quality criteria are conformity to the target structure, accessibility of the one-dimensional channels, and availability of open magnesium sites. These characteristics provide the basis for subsequent investigations of adsorption and

thermodynamic properties. In particular, reliable interpretation requires separation of crystal morphology, accessible pore architecture, and the availability of metal coordination positions. These complementary descriptors should guide comparisons between preparation routes and future material-development studies.

References

1. Caskey, S. R., Wong-Foy, A. G., and Matzger, A. J. Dramatic Tuning of Carbon Dioxide Uptake via Metal Substitution in a Coordination Polymer with Cylindrical Pores //Journal of the American Chemical Society, 2008, 130, 10870-10871. DOI: 10.1021/ja8036096.
2. Wu, X., Bao, Z., Yuan, B., Wang, J., Sun, Y., Luo, H., and Deng, S. Microwave synthesis and characterization of MOF-74 (M=Ni, Mg) for gas separation //Microporous and Mesoporous Materials, 2013, 180, 114-122. DOI: 10.1016/j.micromeso.2013.06.023.
3. Yang, D.-A., Cho, H.-Y., Kim, J., Yang, S.-T., and Ahn, W.-S. CO_2 capture and conversion using Mg-MOF-74 prepared by a sonochemical method //Energy & Environmental Science, 2012, 5, 6465-6473. DOI: 10.1039/C1EE02234B.
4. Stavila, V., et al. IRMOF-74(n)-Mg: a novel catalyst series for hydrogen activation and hydrogenolysis of C-O bonds //Chemical Science, 2019, 10, 9880-9892. DOI: 10.1039/C9SC01018A.
5. Dietzel, P. D. C., Blom, R., and Fjellvåg, H. Base-Induced Formation of Two Magnesium Metal-Organic Framework Compounds with a Bifunctional Tetratopic Ligand //European Journal of Inorganic Chemistry, 2008, 23, 3624-3632. DOI: 10.1002/ejic.200701284.
6. DeCoste, J. B., et al. The effect of water adsorption on the structure of the carboxylate containing metal-organic frameworks Cu-BTC, Mg-MOF-74, and UiO-66 //Journal of Materials Chemistry A, 2013, 1, 11922-11932. DOI: 10.1039/C3TA12497E.

7. Voskanyan, A. A., Goncharov, V. G., Novendra, N., Guo, X., and Navrotsky, A. Thermodynamics Drives the Stability of the MOF-74 Family in Water //ACS Omega, 2020, 5, 13158–13163. DOI: 10.1021/acsomega.0c01189.
8. Thommes, M., Kaneko, K., Neimark, A. V., Olivier, J. P., Rodriguez-Reinoso, F., Rouquerol, J., and Sing, K. S. W. Physisorption of gases, with special reference to the evaluation of surface area and pore size distribution (IUPAC Technical Report) //Pure and Applied Chemistry, 2015, 87, 1051–1069. DOI: 10.1515/pac-2014-1117.